

DESCRIPTION

DECODERZ-202 JOINT FILLER – SILICONE, white cement based, silicone and polymer additives, convenient handling, high resistance to cracking and joint filler material containing chemical additives increases the durability of the color.
Product Class: CG2 WA

APPLICATION AREAS

- Indoor and outdoor floor and wall coverings 1-16 mm grout joints between tiles can be used safely used.

TECHNICAL SPECIFICATIONS

- Appearance / Color : White powder
- Density : 1,10±0,2 kg/l
- Flexural Strength : ≥ 2.5 N/mm²
- Compressive Strength : ≥ 15 N/mm²
- Shrinkage : ≤ 3 mm/m
- Water Absorption, 30 min. After : ≤ 5 g.
240 min. After : ≤ 10 g.
- Abrasion Resistance : ≤ 2000 mm³
- Pot Life : 3 hours

It is produced according to TS EN 13888 CG2WA class.

SURFACE PREPARATION

- Application surface, neat, clean, non-fixed loose parts, flowering and should be cleaned from dust, must be intact.

APPLICATION CONDITIONS

- Substrate and ambient temperature must be between +5°C and +30°C.
- In places subject to direct sunlight, rain and strong winds, the application should be avoided.
- Frozen, melting or there is risk of frost within 24 hours of application surfaces should be avoided.
- Grout must be cured prior to application of the adhesive.

APPLICATION

- DECODERZ-202 JOINT FILLER - SILICONE, clean, cold water were slowly added into the mixer with a low speed for 5-10 minutes until it is lump-free mix. The amount of water required is 6,4-7,6 l. for 20 kg. The amount of water in these rates should be set according to weather conditions. Mortar mixed for 5 minutes and mix again for 1-2 minutes.
- Prepared to apply the mixture with a spatula, spread the floor with rubber or rubber-tipped. Cross and parallel movements in the direction of the joint ranges gaps are filled.
- 1 hour after the surface wiped with a wet cloth or sponge. After completion of the specialized deletion polished surface with a dry cloth.
- Service Period: 24 hours on the wall, on the floor for 48 hours.
- Skinning Time: 15-20 minutes.
- Do not use the material hardened, by adding water.
- Tools used are cleaned with water immediately after application.

Otherwise, DECOSTONE Construction Chemicals Co. cannot be responsible for any damages caused by using the product against our instructions or for inappropriate purposes.

DRYING TIME

Surface dry, at 20 °C and 65% relative humidity for 1 day.

CONSUMPTION

3 mm. applied to the cap making sure that the joint according to the size range 250 to 1500 g/m² (application depth 10 mm.).

Ceramic Dimensions	Joint Consumption Quantities based on the range (g/ m ²)			
	3 mm	4 mm	5 mm	6 mm
10x10	700	950	1200	1500
20x20	350	500	600	720
30x30	250	300	450	520

STORAGE AND SHELF LIFE

Original, unopened package, humid and dry environments stack up to 8, the date of production from 12 months.

PACKAGING

20 kg Craft Bag.

8 layers stacked on pallets 64, 1280 kg.

Pallet size: 110 cm x 110 cm.

SAFETY INFORMATION

During the handling and storage; eyes, mouth, skin and foods should be careful not to contact. In contact with skin and eyes should be washed with plenty of water.

Avoid contact with skin and eyes because it contains cement. If contacted, rinse with plenty of water.

It is recommended to use rubber gloves when applying the product.

Product should not be directly inhaled. If necessary, use a dust mask.

Keep out of the reach of children.

If necessary, consult your doctor.